



PIEFFE NAPEK 70

CARATTERISTICHE DELL'ELASTOMERO <i>PROPERTIES OF THE ELASTOMER</i>	UNITA' DI MISURA <i>MEASUREMENT UNIT</i>	VALORE <i>VALUE</i>
DUREZZA <i>HARDNESS</i>	Shore A	71
CARICO A ROTTURA <i>TENSILE STRENGTH</i>	Kg/cm ²	16,5
LACERAZIONE <i>TEAR STRENGTH</i>	N/mm	49
RESISTENZA AL FREDDO <i>COLD RESISTANCE</i>	°C	-45
DEFORMAZIONE PERMAN. <i>COMPRESSION SET</i>	%	2
INVECCHIAMENTO IN STUFA A CIRCOLAZIONE D'ARIA FORZATA 70 h @ 100°C <i>AGING IN AIR FORCED CIRCULATING OVEN 72 h @ 200°C ASTM</i>		
VARIAZIONE DUREZZA <i>HARDNESS VARIATION</i>	Pt. Shore A	+2
VARIAZIONE CARICO ROTTURA <i>TENSILE STRENGTH VARIATION</i>	%	-11
VARIAZIONE ALLUNG. A ROTTURA <i>ELONGATION AT BREAK VARIATION</i>	%	-25

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.