



## PIEFFE NIPEK 60

CARATTERISTICHE DELL'ELASTOMERO <i>PROPERTY OF THE ELASTOMER</i>	UNITA' DI MISURA <i>MEASUREMENT UNIT</i>	VALORE <i>VALUE</i>
DUREZZA <i>HARDNESS</i>	Sh A	60
CARICO A ROTTURA <i>TENSILE STRENGTH</i>	Kg/cm <sup>2</sup>	12,6
LACERAZIONE <i>TEAR STRENGTH</i>	Kg/mm	37,6
DEFORMAZIONE PERMAN. <i>COMPRESSIONE SET</i>	%	55
RESISTENZA AL FREDDO <i>COLD RESISTANCE</i>	°C	-39
RESISTENZA OZONO <i>OZONE RESISTANCE</i>	I.M.2 All. 20% 70 h @ 35°C	OK
INVECCHIAMENTO IN FLUIDO 15 W 70 h @ 125 °C <i>AGING IN FLUID 15 W 70 h @ 125 °C</i>		
VARIAZIONE DUREZZA <i>HARDNESS VARIATION</i>	Pt. Shore A	-7
VARIAZIONE CARICO ROTTURA <i>TENSILE STRENGTH VARIATION</i>	%	-27,5
VARIAZIONE VOLUME <i>VOLUME VARIATION</i>	%	+9,2

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.