



PIEFFE VIPEK75

CARATTERISTICHE <i>Properties</i>	UNITA' DI MISURA <i>Measurement unit</i>	NORMA <i>Test method</i>	VALORE <i>Value</i>
PESO SPECIFICO APPARENTE <i>Specific gravity</i>	gr/cm ³	-	2,02
DUREZZA <i>Hardness</i>	Shore A	ASTM D-2240	72
CARICO A ROTTURA <i>Tensile strength</i>	MPa	ASTM D-412	13
LACERAZIONE <i>Tear strength</i>	KN/m	ASTM D-624/B	29
ALLUNGAMENTO A ROTTURA <i>Elongation at break</i>	%	ASTM D-412	220
DEFORMAZIONE PERMANENTE <i>Compression Set</i>	%	ASTM D-395 Met B/1	25
TEMP. UTILIZZO SUL L.T. <i>Service Temp. long Term</i>	°C	-	205
TEMP. UTILIZZO SUL B.T. <i>Service Temp. short Term</i>	°C	-	260
INVECCHIAMENTO ARIA 250°C @ 7 gg - Ageing Air 250°C x 7 gg			
VARIAZIONE DUREZZA <i>HARDNESS VARIATION</i>	Pt. Shore A	D-573	+1
VARIAZIONE CARICO A <i>TENSILE STRENGTH VARIATION</i>	%	D-573	-10
VARIAZIONE ALLUNGAMENTO <i>ELONGATION AT BREAK VARIATION</i>	%	D-573	-13
INVECCHIAMENTO OLIO IRM 903 175°C @ 70 h - Ageing IRM 902 Oil 175°C @ 70 h			
VARIAZIONE DUREZZA <i>HARDNESS VARIATION</i>	Pt. Shore A	D-471	-2
VARIAZIONE CARICO A <i>TENSILE STRENGTH VARIATION</i>	%	D-471	-13
VARIAZIONE ALLUNGAMENTO <i>ELONGATION AT BREAK VARIATION</i>	%	D-471	+10
VARIAZIONE VOLUME <i>VOLUME VARIATION</i>	%	D-471	+2,0

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.