

**PIEFTE MGP20**

CARATTERISTICHE DELL'ELASTOMERO <i>PROPERTIES</i>	NORMA ASTM/ISO/DIN	UNITA' DI MISURA <i>MEASUREMENT UNIT</i>	VALORE <i>VALUE</i>
DUREZZA <i>HARDNESS</i>	DIN 53505	Sh A	20
MODULO AL 100 % DI ALL. <i>MODULUS 100%</i>	DIN 53504	Mpa	0,12
MODULO AL 300 % DI ALL. <i>MODULUS 300%</i>	DIN 53504	Mpa	2,7
RESISTENZA A TRAZIONE <i>TENSILE STRENGTH</i>	DIN 53504	Mpa	5,1
ALLUNGAMENTO A ROTTURA <i>ELONGATION AT BREAK</i>	DIN 53504	%	252
RESISTENZA ALLA LACERAZIONE <i>TEAR STRENGTH</i>	DIN 53515	K N/m	15
RESISTENZA AL TAGLIO <i>TEAR STRENGTH (with cut)</i>	DIN 53515	K N/m	4,8
RESILIENZA <i>TEAR STRENGTH (Die C)</i>	DIN 53512	%	13
DEFORMAZIONE PERMANENTE <i>COMPRESSION SET</i>	DIN 53517	%	1,2
ABRASIONE <i>ABRASION SET</i>	DIN 53516	mm ³	115

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.