



## PIEFFE P700 D

CARATTERISTICHE <i>Properties</i>	NORMA <i>Test method</i>	UNITA' DI MISURA <i>Measurement unit</i>	VALORE <i>Value</i>
DUREZZA <i>Hardness</i>	ASTM D-2240	Sh D	75
MODULO AL 100 % DI ALL. <i>Modulus 100%</i>	ASTM D-412 Tirato a 8,5 mm/s <i>Pulled at 20 in /min</i>	Mpa	37,9
MODULO AL 200 % DI ALL. <i>Modulus 200%</i>	ASTM D-412 Tirato a 8,5 mm/s <i>Pulled at 20 in /min</i>	Mpa	44,8
CARICO A ROTTURA <i>Tensile strength</i>	ASTM D-412 Tirato a 8,5 mm/s <i>Pulled at 20 in /min</i>	Mpa	51,7
ALLUNGAMENTO A ROTTURA <i>Elongation at break</i>	ASTM D-412 Tirato a 8,5 mm/s <i>Pulled at 20 in /min</i>	%	230
RIMBALZO ELASTICO <i>Resilience Rebound</i>	ASTM D-2632	%	25,4
RESISTENZA ALLA LACERAZIONE <i>Tear strength</i>	ASTM D-470	K N/m	166
PERDITA ALL'ABRASIONE <i>Abrasion Loss</i>	DIN 53516	mm <sup>3</sup>	93
RESISTIVITA' SPECIFICA <i>Surface Resistivity</i>	DIN EN 60093	Ω · cm	10 <sup>12</sup>

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.