

**PIEFTE UNF90**

CARATTERISTICHE DELL'ELASTOMERO <i>PROPERTY OF THE ELASTOMER</i>	UNITA' DI MISURA <i>MEASUREMENT UNIT</i>	NORMA ASTM/ISO/DIN	VALORE <i>VALUE</i>
DUREZZA <i>HARDNESS</i>	Sh A	DIN53505	90
CARICO A ROTTURA <i>TENSILE STRENGTH</i>	Mpa	DIN53504	39
ALLUNGAMENTO A ROTTURA <i>ELONGATION AT BREAK</i>	%	DIN53504	503
RESISTENZA ALLA LACERAZIONE (senza intaglio) <i>TEAR STRENGTH unnotched</i>	KN/m	DIN53515	140
RESISTENZA ALLA LACERAZIONE (con intaglio) <i>TEAR STRENGTH notched</i>	KN/m	DIN53515	43
RESILIENZA <i>RESILIENCE</i>	%	DIN53512	53
DENSITA' <i>DENSITY</i>	Gr/cm ³	-	1,11
PERDITA ALL'ABRASIONE <i>ABRASION LOSS</i>	mm ³	DIN53516	58
MODULO AL 100% DI ALLUNGAMENTO <i>MODULUS 100%</i>	Mpa	DIN53504	9,9
MODULO AL 200% DI ALLUNGAMENTO <i>MODULUS 200%</i>	Mpa	DIN53504	13,7
MODULO AL 300% DI ALLUNGAMENTO <i>MODULUS 300%</i>	Mpa	DIN53504	18,2

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.