

**PIEFFE UNF Com90**

| CARATTERISTICHE DELL'ELASTOMERO <i>PROPERTIES</i> | NORMA ASTM/ISO/DIN | UNITA' DI MISURA <i>MEASUREMENT UNIT</i> | VALORE <i>VALUE</i> |
|--|-----------------------|---|--------------------------|
| DUREZZA <i>HARDNESS</i> | ASTM D-2240 | Shore A | 90 |
| CARICO A ROTTURA <i>TENSILE STRENGTH</i> | ASTM D-412 | Kg/cm ² | 183 |
| ALLUNGAMENTO A ROTTURA <i>ELONGATION AT BREAK</i> | ASTM D-412 | % | 312 |
| RESISTENZA ALLA LACERAZIONE <i>TEAR STRENGTH</i> | ASTM D-624 C | Kg/cm | 39 |
| MODULO 100% <i>MODULUS 100%</i> | ASTM D-412 | Kg/cm ² | 66 |
| MODULO 200% <i>MODULUS 200%</i> | ASTM D-412 | Kg/cm ² | 127 |
| DENSITA' <i>DENSITY</i> | - | gr/cm ³ | 1,22 |
| COLORE <i>COLOUR</i> | - | - | NEUTRO <i>NEUTRAL</i> |

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.