



PIEFTE VIPEK F70

SECONDO FDA 21 CFR 177.2600

CARATTERISTICHE <i>Properties</i>	NORMA <i>Test method</i>	UNITA' DI MISURA <i>Measurement unit</i>	VALORE <i>Value</i>
PESO SPECIFICO APPARENTE <i>Specific gravity</i>	-	gr/cm ³	2,33
DUREZZA <i>Hardness</i>	ASTM D-2240	Shore A	73
CARICO A ROTTURA <i>Tensile strength</i>	ASTM D-412	MPa	12,5
ALLUNGAMENTO A ROTTURA <i>Elongation at break</i>	ASTM D-412	%	190
RESISTENZA ALLA LACERAZIONE <i>Tear strength</i>	ASTM D-624/B	KN/m	35
DEFORMAZIONE PERMANENTE <i>Compression Set</i>	ASTM D-395 Met B/1	%	18

RIGONFIAMENTI IN FLUIDI DI IMPIEGO ALIMENTARE *Swellings in fluid of food employment*

FLUIDO <i>Fluid</i>	TEMP. °C <i>Temp. °C</i>	DURATA gg <i>Duration dd</i>	VARIAZ. VOL.% <i>Variation vol. %</i>
ACQUA <i>water</i>	70	180	+3
OLIO D'OLIVA <i>olive oil</i>	20	7	+4
GLICERINA <i>glycerine</i>	70	28	-0,6
ETANOLO <i>ethanole</i>	20	28	+8
ACETO DI VINO <i>wine's vinegar</i>	20	3	+1,5

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that PIEFFE srl cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of PIEFFE srl products in any given application.